



ETHAFOAM® 220

POLYETHYLENE FOAM

ETHAFOAM® 220 polyethylene foam is a strong, resilient, medium-density 2.2 pcf (35.2 kg/m³), closed-cell foam. It is ideally suited as a component material in products requiring a shock absorbing, vibration dampening, insulating and/or buoyancy component, and as a material for cushioning components in packaging applications for loadings up to 2.5 psi (17.5 kPa).

ETHAFOAM 220 has outstanding recovery characteristics that provide optimal cushioning protection against repeated impacts. It is ideal for cushion packaging and is used in many applications, including computer, automotive, construction and recreation. To achieve optimum performance, Sealed Air recommends that qualified packaging engineers design the total packaging solution.

Sizes Available in Black

(Planks):

2" x 48" x 108" 4" x 48" x 108"

Sizes Available in Natural

(Planks):

1.5" x 48" x 108" 2" x 48" x 108" 2.5" x 48" x 108"
3" x 48" x 108" 4" x 24" x 108" 4" x 48" x 108"

Flammability

ETHAFOAM® 220 polyethylene foam has successfully passed FMVSS 302 flammability testing, conducted according to the U.S. Code of Federal Regulations, CFR 49.

Benefits of ETHAFOAM® 220

ETHAFOAM® 220 polyethylene foam is a durable, lightweight, flexible, solid extruded product. As the properties listed on the reverse suggest, ETHAFOAM 220 offers excellent strength, resistance to creep under load, vibration and shock absorbency, and water resistance characteristics.

ETHAFOAM 220 is produced with a patented process. This process delivers a higher quality product with improved dimensional stability and safety. This process technology incorporates a patented CFC- and HCFC-free blowing agent system and an accelerated curing system that reduces residual blowing agents in ETHAFOAM products to trace amounts.

ETHAFOAM 220 meets the requirements of the U.S. Clean Air Act Amendments. It is easily fabricated, impervious to most chemicals, non-abrasive and performs consistently over a wide range of temperatures.

ETHAFOAM 220 is also reusable and completely recyclable because it is made of non-crosslinked polyethylene.

ETHAFOAM[®] 220

POLYETHYLENE FOAM

Physical Properties of ETHAFOAM[®] 220 Polyethylene Foam

PHYSICAL PROPERTIES†	TEST METHOD	DIRECTION	VALUE
Density	ASTM D3575, Suffix W, Method B; ISO 845		pcf (kg/m ³) 2.2 (35.2)
Compression Set	ASTM D3575, Suffix B (50% compr.); EN/ISO 1856 (23°C, 25% compr.)	Vertical	< 20% < 10%
Compressive Creep (1000 hrs @ 73°F [23°C])	ASTM D3575, Suffix BB	Vertical	< 10% @ 2.5 psi (17.5 kPa)
Compressive Deflection @ 10% @ 25% @ 50%	ASTM D3575, Suffix D	Average	psi (kPa) 7 (50) 9 (65) 18 (124)
Thermal Stability	ASTM D3575, Suffix S; ISO 2796		<1.5% <2%
Thermal Conductivity @ 75°F (24°C) @ 23°F (-5°C)	ASTM D3575, Suffix V; EN 28301; ISO 2581	Vertical	BTU•in/hr•ft ² •°F (W/m ² K) 0.42 (0.06) 0.37 (0.05)
Water Absorption	ASTM D3575, Suffix L; ISO 2896; ASTM C272		lb/ft ² (kg/m ²) 0.3 (1.5) < 3% by volume
Buoyancy	ASTM D3575, Suffix AA		pcf (kg/m ³) 58 (930)
Tensile Strength @ peak	ASTM D3575, Suffix T; ISO 1798	Average	psi (kPa) 32 (220)
Tensile Elongation	ASTM D3575, Suffix T; ISO 1798	Average	50%
Tear Strength	ASTM D3575, Suffix G	Average	lb/in (N/mm) 10 (1.75)

†The data presented for this product are for unfabricated ETHAFOAM polyethylene foam products. While values shown are typical of the product, they should not be construed as specification limits.



Specialty Materials

2401 Dillard Street | Grand Prairie, Texas 75051

Tel: 866.795.3028 | Fax: 866.795.3045

Distributed By:

Corporate Office: Sealed Air Corporation

200 Riverfront Blvd., Elmwood Park, NJ 07407 www.sealedair.com

© Reg. U.S. Pat. Off. © Sealed Air Corporation 2008. All rights reserved. Printed in the U.S.A.

S14-V1-01/08